



Toll Free 1-800-801-2778  
 Local 1-813-223-7673  
 Mon-Fri 8am to 5pm EST

Website: [www.FirstChoiceMarineSupply.com](http://www.FirstChoiceMarineSupply.com) Email: [Sales@FirstChoiceMarineSupply.com](mailto:Sales@FirstChoiceMarineSupply.com)

NON – ROTATING STEEL WIRE ROPE - ROPE GALVANIZED OR BRIGHT 19 X 7 Bright IWRC EIPS		
DIAMETER IN INCHES	APPROX. WEIGHT PER FOOT IN POUNDS	BREAKING STRENGTH IN TONS
1/4	0.113	2.77
5/16	0.177	4.3
3/8	0.25	6.15
7/16	0.35	8.33
1/2	0.45	10.8
9/16	0.58	13.6
5/8	0.71	16.8
3/4	1.02	24.0
7/8	1.39	32.5
1	1.82	42.2
1 1/8	2.3	53.1
1 1/4	2.85	65.1

NON – ROTATING STEEL WIRE ROPE - ROPE GALVANIZED OR BRIGHT 8 x 25 Bright IWRC EIPS		
DIAMETER IN INCHES	APPROX. WEIGHT PER FOOT IN POUNDS	BREAKING STRENGTH IN TONS
3/8	0.26	6.63
1/2	0.47	11.6
9/16	0.60	14.7
5/8	0.73	18.1
3/4	1.06	25.9
7/8	1.44	35.0
1	1.88	45.5

- Tables are for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of listed breaking strength.
  - Made in accordance with federal specification RR-W-410F. Meets the performance requirements of API-9A, and proposed ASTM.



Toll Free 1-800-801-2778  
 Local 1-813-223-7673  
 Mon-Fri 8am to 5pm EST

Website: [www.FirstChoiceMarineSupply.com](http://www.FirstChoiceMarineSupply.com) Email: [Sales@FirstChoiceMarineSupply.com](mailto:Sales@FirstChoiceMarineSupply.com)

NON – ROTATING STEEL WIRE ROPE – GALVANIZED 35 X 7 Drawn Galvanized 2160 grade, RHLL & IWRC		
SIZE IN MM	POUNDS/FT	BREAKING STRENGTH IN POUNDS
10	0.31	21,131
12	0.45	31,921
13	0.54	38,216
14	0.62	44,285
16	0.8	57,099
18	1.01	73,060
19	1.14	82,052
20	1.29	89,246
22	1.56	106,780
24	1.85	127,012
25.4	2.1	136,000
26	2.16	147,918
28	2.55	170,848
30	2.92	198,048
32	3.31	223,226
34	3.73	254,698
36	4.19	286,170
38	4.62	314,720

- Tables are for comparison only. Actual operating loads may vary, but should never exceed the recommended design factor or 20% of listed breaking strength.
  - Made in accordance with federal specification RR-W-410F. Meets the performance requirements of API-9A, and proposed ASTM.